

Revolve® N-265

PE

Matrix Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Yield stress	15.7	MPa	ISO 527
Flexural modulus, 23°C	605	MPa	ISO 178
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	46	°C	ISO 75-1/-2
Other properties			
Density	935	kg/m ³	ISO 1183

Characteristics**Processing**

Rotational Molding

Delivery form

Pellets, Powder, Black, Natural Color

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Features

Blending Resin

Chemical Resistance

General Chemical Resistance, Environmental Stress Crack Resistance

Applications

General Purpose

Regional Availability

Europe, Asia Pacific