

**Revolve® XL400 Black**

PE

Matrix Polymers

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Yield stress	<b>21</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>850</b>	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	<b>60</b>	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	<b>955</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Rotational Molding

**Features**

Crosslinkable

**Delivery form**

Powder, Black

**Chemical Resistance**

General Chemical Resistance

**Special Characteristics**

High impact or impact modified

**Regional Availability**

Europe, Asia Pacific