

LOXILLOY PC/ABS 1125-20 UV3 IM3 05016

(PC+ABS)

Loxim Industries Limited

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Mechanical properties			
ISO Data			
Yield stress	50	MPa	ISO 527
Yield strain	5	%	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	2700	MPa	ISO 178
Flexural strength	85	MPa	ISO 178
Izod notched impact strength, +23°C	45	kJ/m ²	ISO 180/1A
Izod notched impact strength	38	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	105	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	125	°C	ISO 75-1/-2
Vicat softening temperature, B	125	°C	ISO 306
Other properties			
Density	1130	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	100 - 110	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	275 - 300	°C	-
Mold temperature	60 - 90	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Ductile

Chemical Resistance

General Chemical Resistance

Applications

Automotive, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific