

MABLEX® 468

(PC+ABS)

Ravago Group

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Yield stress	60	MPa	ISO 527
Stress at break	50	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Izod notched impact strength, +23°C	60	kJ/m ²	ISO 180/1A
Izod notched impact strength	30	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Vicat softening temperature, B	137	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
Glow Wire Flammability Index (GWFI)	850	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-
Other properties			
Density	1160	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Regional Availability

Europe