

MAC-501DY

(PC+ABS)

Kingfa Sci. & Tech.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	55	MPa	ASTM D 638
Elongation at Break	50	%	ASTM D 638
Flexural Modulus	2240	MPa	ASTM D 790
Flexural Strength	81	MPa	ASTM D 790
Rockwell Hardness	R 115	-	ASTM D 785
Izod Impact notched, 1/8 in	437	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	N	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 66 psi	124	°C	ASTM D 648
DTUL @ 264 psi	108	°C	ASTM D 648
Electrical properties			
ASTM Data			
Dielectric Strength, Short Time	28	kV/mm	ASTM D 149
Surface Resistivity	1E15	Ohm	ASTM D 257
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Other properties			
Water Absorption, 24hr	0.1	%	ASTM D 570
Density	1130	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Applications

Automotive, Electrical and Electronical

Delivery form

Pellets

Regional Availability

Asia Pacific

Special Characteristics

Platable, High impact or impact modified