

**MAC-601 DY**

(PC+ABS)

Kingfa Sci. &amp; Tech.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.006</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>50</b>	MPa	ASTM D 638
Elongation at Break	<b>80</b>	%	ASTM D 638
Flexural Modulus	<b>2250</b>	MPa	ASTM D 790
Flexural Strength	<b>80</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>615</b>	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	<b>510</b>	J/m	ASTM D 256
Temperature	<b>-30</b>	°C	-
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>1.6</b>	mm	-
DTUL @ 66 psi	<b>124</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>108</b>	°C	ASTM D 648
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>28</b>	kV/mm	ASTM D 149
Surface Resistivity	<b>1E15</b>	Ohm	ASTM D 257
Volume Resistivity	<b>&gt;1E15</b>	Ohm*cm	ASTM D 257
<b>Other properties</b>			
Water Absorption, 24hr	<b>0.1</b>	%	ASTM D 570
Density	<b>1140</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

Platable, High impact or impact modified

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

Asia Pacific