

OPTIX® CP - 51 KC CLEAR

PMMA

Plaskolite West, Inc.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	3.8	kg	-
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2890	MPa	ASTM D 638
Tensile Strength	55.8	MPa	ASTM D 638
Flexural Strength	102	MPa	ASTM D 790
Izod Impact notched, 1/4 in	18	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Coefficient of Thermal Expansion, MD	60	E-6/K	ASTM D 696
DTUL @ 264 psi	76	°C	ASTM D 648
Vicat Temperature	94	°C	ASTM D 1525

Optical properties	Value	Unit	Test Standard
ASTM Data			
Haze	1	%	ASTM D 1003
Light Transmittance	92	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Applications

General Purpose

Regional Availability

North America