

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	3.8	kg	-
Mechanical properties			
ASTM Data			
Izod Impact notched, 1/8 in	42.7	J/m	ASTM D 256
Optical properties			
ASTM Data			
Haze	2.5	%	ASTM D 1003
Light Transmittance	88	%	ASTM D 1003
Other properties			
Density	1150	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America, South and Central America