

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	3.8	kg	-
Mold Shrinkage, MD	0.0055	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	3227	MPa	ASTM D 638
Elongation at Break	5.8	%	ASTM D 638
Flexural Modulus	3241	MPa	ASTM D 790
Rockwell Hardness	M 94	-	ASTM D 785
Izod Impact notched, 1/8 in	16	J/m	ASTM D 256
Thermal properties			
ASTM Data			
Vicat Temperature	97.2	°C	ASTM D 1525
Optical properties			
ASTM Data			
Light Transmittance	85	%	ASTM D 1003
Other properties			
Water Absorption, 24hr	0.4	%	ASTM D 570
Density	1180	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America, South and Central America