

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	1.8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	3.8	kg	-
Mold Shrinkage, MD	0.0045	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Modulus	2413	MPa	ASTM D 638
Elongation at Break	35	%	ASTM D 638
Flexural Modulus	2413	MPa	ASTM D 790
Rockwell Hardness	M 68	-	ASTM D 785
Izod Impact notched, 1/8 in	32	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
Vicat Temperature	97.2	°C	ASTM D 1525
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	2	%	ASTM D 1003
Light Transmittance	92	%	ASTM D 1003
Index of Refraction	1.49	-	ASTM D 542
<b>Other properties</b>			
Water Absorption, 24hr	0.3	%	ASTM D 570
Density	1170	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Special Characteristics

Transparent

### Regional Availability

North America, South and Central America