

Product Texts

Productprofil:

PLEXIGLAS® Softlight zk6BR df23, based on PLEXIGLAS® Resist zk6BR, is an impact modified molding compound characterized by diffuse scattering of light.

Typical properties of impact modified PLEXIGLAS® molding compound are

1. high break resistance and impact strength
2. improved resistance to stress cracking
3. good weather resistance
4. high surface hardness and mar resistance
5. the pleasant feel and sound of the moldings.

PLEXIGLAS® Softlight zk6BR df23 is characterized by the following special properties:

1. excellent lightdiffusion combined with excellent light transmission
2. matte surfaces can be obtained by varying the extrusion parameters.

Application:

Used for extruding profiles and sheets, but also for injection molding items for lighting engineering applications

Example:

applications that call for light diffusion combined with optimum transmission

Processing:

PLEXIGLAS® Softlight zk6BR df23 can be processed on extruders with 3-zone general purpose screws for engineering thermoplastics. The matte finish of profile surfaces depends very much on machine design (calibrating unit, polishing rolls) and cooling conditions. It can be enhanced by controlled temperature reduction.

Physical Form / Packaging:

PLEXIGLAS® Softlight df molding compounds are supplied as pellets of uniform size, packaged in 25kg polyethylene bags; other packaging on request.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	1.3	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	3.8	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	1900	MPa	ISO 527
^[C] Yield stress	46	MPa	ISO 527
^[C] Yield strain	5	%	ISO 527
^[C] Nominal strain at break	36	%	ISO 527
^[C] Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Glass transition temperature, 10°C/min	109	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	93	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	99	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	99	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	90	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	1E13	Ohm	IEC 62631-3-2

[C]: CAMPUS

Optical properties	Value	Unit	Test Standard
ISO Data			
^[C] Luminous transmittance	81	%	ISO 13468-1, -2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1150	kg/m ³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	255	°C	ISO 294
Injection Molding, mold temperature	51	°C	ISO 294
Injection Molding, injection velocity	195	mm/s	ISO 294

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Profile Extrusion, Sheet Extrusion, Other Extrusion

Delivery form

Pellets

Additives

Release agent

Special Characteristics

High impact or impact modified, Light stabilized or stable to light, U.V. stabilized or stable to weather

Features

Light Diffusing

Chemical Resistance

Environmental Stress Crack Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Injection molding

PREPROCESSING

Predrying temperature: max. 85 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Melt temperature: 220 - 260°C

Mold temperature: 60 - 90°C

Profile extrusion

PREPROCESSING

Predrying temperature: max. 85 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Melt temperature: 230 - 260 °C

Die temperature: 230 - 260 °C

Sheet extrusion

PREPROCESSING

Predrying temperature: max. 85 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Melt temperature: 230 - 260 °C

Die temperature: 230 - 260 °C