

Product Texts**Productprofil**

PLEXIGLAS® Resist AG 100 is an amorphous thermoplastic molding compound, based on impact-modified polymethyl methacrylate (PMMA).

PLEXIGLAS® molding compounds have the following typical properties:

- high weather resistance
- excellent transmission and clarity
- brilliant appearance
- low weight – half the weight of glass
- 100% recyclable – best life cycle assessment as compared with glass and PC
- the pleasant feel and sound of the molded parts.

PLEXIGLAS® Resist AG 100 is characterized by the following special properties:

- highest breaking strength and impact strength (30 times higher breaking strength than glass)
- improved resistance to stress cracking
- balanced property profile
- clear reduction of reversible haze at very high and low temperatures
- increased heat deflection temperature under load
- AMECA listing, CAMPUS and moldflow data available

Application and approvals

PLEXIGLAS® Resist AG 100 has a balanced property profile and was specially developed for automotive glazing. This specialty molding compound meets all the relevant requirements for this field of application.

Apart from reducing the vehicle weight, injectionmolded glazing offers maximum freedom of design and functional integration, such as the integration of lighting or panel trim. An approval to ECE R43 is required for use as automotive glazing. The material has undergone and passed all tests in line with ECE R43.

The test report of the Materials Testing Agency in North Rhine-Westphalia is available for systems based on PLEXIGLAS® Resist AG 100 for rear side windows, roof and rear windows. Further details are available on request.

Processing

PLEXIGLAS® Resist AG 100 can be processed by injection molding of parts or by sheet extrusion and coextrusion. PLEXIGLAS® Resist AG 100 can be injection-molded on processing machines with a standard three-section screw for engineering thermoplastics in one-component or twocomponent processes.

FabricationForming after extrusion

The forming conditions are the same as for extruded PLEXIGLAS®. The high optical quality of the surface after forming is also comparable. Predrying is not necessary in most cases. During heating, the material turns slightly white, but this disappears completely upon cooling.

Painting and screen printing

In principle, the same paints and lacquers can be used as for extruded PLEXIGLAS®. However, we recommend that you carry out preliminary tests in this case.

Coating

Surface coating, for example with polysiloxane systems, can be carried out by means of conventional processes.

Please send any questions on fabrication to automotive-glazing@evonik.com.

Physical Form / Packaging

PLEXIGLAS® Resist molding compounds are supplied as pellets of uniform size in 25kg polyethylene bags or 500kg boxes with PE lining. Other types of packaging are available on request.

Colors

PLEXIGLAS® Resist AG 100 for vehicle glazing is available in Clear-transparent (9V913). Beyond this, the transparent colors Green (6V176) and Gray (7V275) are available. Further colors on request: automotive-glazing@evonik.com

Sustainability

From production to recycling, the environmental impact of PLEXIGLAS® was tested in the life cycle assessment in accordance with ISO 14040ff and received a positive rating. In addition to its durability, PLEXIGLAS® offers convincing recyclability. It can be completely recycled by chemical conversion to its starting materials or directly reused.

Thus, in a study prepared by PE International AG, the environmental impacts during manufacture, application and disposal of automotive glazing made from PLEXIGLAS® were positively rated in comparison with reference systems (single-layer safety glass, laminated safety glass, PC). We will be pleased to provide more details on request.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	1.1	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	3.8	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2200	MPa	ISO 527
^[C] Yield stress	55	MPa	ISO 527
^[C] Yield strain	5	%	ISO 527
^[C] Nominal strain at break	45	%	ISO 527
^[C] Charpy impact strength, +23°C	120	kJ/m ²	ISO 179/1eU

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Glass transition temperature, 10°C/min	112	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	100	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	105	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	105	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Optical properties	Value	Unit	Test Standard
ISO Data			
^[C] Luminous transmittance	91	%	ISO 13468-1, -2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	1.5	%	Sim. to ISO 62
^[C] Humidity absorption	0.5	%	Sim. to ISO 62
^[C] Density	1160	kg/m ³	ISO 1183

[C]: CAMPUS

PLEXIGLAS® Resist AG 100

PMMA-I

Röhm GmbH

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	250	°C	ISO 294
Injection Molding, mold temperature	82	°C	ISO 294
Injection Molding, injection velocity	195	mm/s	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	70 - 80	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	235 - 270	°C	-
Mold temperature	60 - 80	°C	-

Characteristics**Processing**

Injection Molding, Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion, Thermoforming

Delivery form

Pellets

Additives

Release agent

Special Characteristics

High impact or impact modified, Light stabilized or stable to light, U.V. stabilized or stable to weather, Transparent

Features

Amorphous

Chemical Resistance

Environmental Stress Crack Resistance

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding****PREPROCESSING**

Predrying temperature: 70 - 80°C

Predrying time in a desiccant-type drier: 3 - 4 h

PROCESSING

Melt temperature: 235 - 270°C

Mold temperature: 60 - 80°C