

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Stress at break	80	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus, 23°C	4500	MPa	ISO 178
Flexural strength	105	MPa	ISO 178
Izod notched impact strength, +23°C	4.5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	160	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	165	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Burning rate, FMVSS, Thickness 1 mm	100	mm/min	ISO 3795 (FMVSS 302)
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	10000	Ohm*m	IEC 62631-3-1
Surface resistivity	100000	Ohm	IEC 62631-3-2
<b>Other properties</b>			
Density	1430	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	70 - 90	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.12	%	-
Melt temperature	170 - 190	°C	-
Mold temperature	70 - 90	°C	-

## Characteristics

### Processing

Injection Molding

### Features

Copolymer

### Additives

Lubricants

### Regional Availability

Europe