

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>14800</b>	MPa	ISO 527
Tensile Strength	<b>90</b>	MPa	ISO 527
Strain at break	<b>0.8</b>	%	ISO 527
Charpy impact strength, +23°C	<b>13</b>	kJ/m <sup>2</sup>	ISO 179/1eU

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>165</b>	°C	ISO 11357-1/-3

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1460</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

<b>Features</b>	<b>Regional Availability</b>
Copolymer	Europe