ALCOM POM 770/1.1 CF20

POM-CF20 MOCOM Compounds GmbH & Co. KG

Product Texts

Base Polymer	Polyoxymethylene Copolymer
Filler/Additive System	20 % carbon fibres
Special Features	electrically conductive,reduced surface resistivity,high stiffness
Market Segment	Automotive,Machinery
Application Area	various
Typical Applications	functional components,bearings

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
[C] Melt volume-flow rate, MVR	**2**	cm³/10min	ISO 1133
Temperature	**190**	°C	-
Load	**2.16**	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	**14500**	MPa	ISO 527
[C] Stress at break	**65**	MPa	ISO 527
[C] Strain at break	**0.6**	%	ISO 527
[C] Charpy impact strength, +23°C	**12**	kJ/m²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	**4.5**	kJ/m²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
[C] Temp. of deflection under load, 1.80 MPa	**155**	°C	ISO 75-1/-2
[C] Vicat softening temperature, B	**156**	°C	ISO 306

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
[C] Surface resistivity	**50**	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Density	**1460**	kg/m³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Special Characteristics

Increased electrical conductivity

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Injection molding

Pre-Drying Conditions	in a dry air (dessiccant) dryer 100-110 °C for 2-3 h in an air circulating dryer 100-110 °C for 3-5 h dependant on moisture content
Processing Injection Moulding	melt temperature 190-230 °C

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.

	mould temperature 60-120 °C
Storage	dry, protected from light not above 30°C

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.