

RTP 885

POM-CF30

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0014	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	17240	MPa	ASTM D 638
Tensile Strength	152	MPa	ASTM D 638
Flexural Modulus	16550	MPa	ASTM D 790
Flexural Strength	234	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	163	°C	ASTM D 648
Electrical properties			
ASTM Data			
Surface Resistivity	100000	Ohm	ASTM D 257
Volume Resistivity	10000	Ohm*cm	ASTM D 257
Other properties			
Density	1480	kg/m ³	ASTM D 792
Moisture Content	0.15	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	2	h	-
Melt temperature	182 - 218	°C	-
Mold temperature	79.4 - 107	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific