

**Product Texts**

Base Polymer	Polyoxymethylene Copolymer
Filler/Additive System	2 % molybdenium disulphide
Special Features	improved sliding / wear
Market Segment	Automotive, Machinery
Application Area	various

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	8	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

[C]: CAMPUS

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2600	MPa	ISO 527
<sup>[C]</sup> Yield stress	60	MPa	ISO 527
<sup>[C]</sup> Yield strain	9	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	165	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	7	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

**Thermal properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	98	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	144	°C	ISO 306

[C]: CAMPUS

**Other properties**

	Value	Unit	Test Standard
<sup>[C]</sup> Density	1410	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information****Injection molding**

Pre-Drying Conditions	in a dry air (dessiccant) dryer 100-110 °C for 2-3 h in an air circulating dryer 100-110 °C for 3-5 h dependant on moisture content
Processing Injection Moulding	melt temperature 180-220 °C mould temperature 60-120 °C
Storage	dry, protected from light not above 30°C