

Product Texts

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

Delrin® 300TE is a toughened medium-high viscosity acetal homopolymer for injection molding with very low VOC emissions for applications in automotive interiors.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	6	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	1.3	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.5	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	1900	MPa	ISO 527
^[C] Yield stress	53	MPa	ISO 527
^[C] Yield strain	20	%	ISO 527
^[C] Nominal strain at break	36	%	ISO 527
^[C] Charpy notched impact strength, +23°C	16	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	10	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	178	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	71	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	132	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	125	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.9	%	Sim. to ISO 62
^[C] Humidity absorption	0.2	%	Sim. to ISO 62
^[C] Density	1380	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding, Profile Extrusion, Sheet Extrusion, Other Extrusion

Delivery form

Pellets, Natural Color

Additives

Lubricants, Release agent

Special Characteristics

High impact or impact modified

Features

Low Emission, Homopolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa