

**DURACON® RB-10**

POM

Polyplastics

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	<b>2.4</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>2.2</b>	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Rockwell hardness	<b>M 80</b>	-	ISO 2039-2
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>87</b>	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	<b>1410</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Regional Availability**

Asia Pacific