

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	12	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.8	%	ISO 294-4, 2577
^[C] Density of melt	1200	kg/m ³	-
^[C] Thermal conductivity of melt	0.155	W/(m K)	-
^[C] Spec. heat capacity of melt	2210	J/(kg K)	-
^[C] Ejection temperature	140	°C	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2900	MPa	ISO 527
^[C] Yield stress	65	MPa	ISO 527
^[C] Yield strain	9	%	ISO 527
^[C] Nominal strain at break	25	%	ISO 527
^[C] Charpy impact strength, +23°C	200	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	200	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	6.5	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	6	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	166	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	106	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	4	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	4	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	20	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	50	E-4	IEC 62631-2-1
^[C] Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	1E14	Ohm	IEC 62631-3-2
^[C] Electric strength	35	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.65	%	Sim. to ISO 62
^[C] Humidity absorption	0.2	%	Sim. to ISO 62
^[C] Density	1410	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Features

Thermal Stability, Copolymer

Delivery form

Pellets

Chemical Resistance

Alkali Resistance, Solvent Resistance, Hydrolytically Stable, Oxidation Resistance

Additives

Release agent

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather