

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	5.5	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	1.8	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.6	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2000	MPa	ISO 527
^[C] Yield stress	50	MPa	ISO 527
^[C] Yield strain	12	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	13	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	8	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	166	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	84	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	148	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	110	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.8	%	Sim. to ISO 62
^[C] Humidity absorption	0.25	%	Sim. to ISO 62
^[C] Density	1380	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Profile Extrusion

Delivery form

Pellets

Additives

Release agent

Features

Copolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa