

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	50	MPa	ISO 527
Strain at break	20	%	ISO 527
Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	166	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	80	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E16	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1420	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Tribologic Grade

Chemical Resistance

General Chemical Resistance

Applications

Automotive, Sports Equipment

Regional Availability

Europe