

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577
Molding shrinkage, normal	1.6	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Stress at break	60	MPa	ISO 527
Strain at break	25	%	ISO 527
Charpy impact strength, +23°C	100	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	178	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	1E16	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
<b>Other properties</b>			
Density	1380	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Features

Tribologic Grade, Homopolymer

### Chemical Resistance

General Chemical Resistance

### Applications

Automotive, Sports Equipment

### Regional Availability

Europe