

Product Texts

LNP LUBRILOY K2000 compound is based on Acetal (POM) resin containing proprietary lubricant. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E207780-101345248](https://www.ulprospector.com/207780-101345248)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	2.2	%	ISO 294-4, 2577
Molding shrinkage, normal	2.1	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	2.2	mm/mm	ASTM D 955
Mold Shrinkage, TD	2.3	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2560	MPa	ISO 527
Yield stress	60	MPa	ISO 527
Yield strain	9	%	ISO 527
Stress at break	59	MPa	ISO 527
Strain at break	13.3	%	ISO 527
Flexural modulus	2420	MPa	ISO 178
Flexural strength	65	MPa	ISO 178
Izod impact strength, +23°C, 4mm	48	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	6	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	2060	MPa	ASTM D 638
Tensile Strength at Yield	55	MPa	ASTM D 638
Tensile Strength at Break	51	MPa	ASTM D 638
Elongation at Yield	9.3	%	ASTM D 638
Elongation at Break	32.4	%	ASTM D 638
Flexural Modulus	2420	MPa	ASTM D 790
Flexural Strength	84	MPa	ASTM D 790
Izod Impact notched, 1/8 in	69	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	1360	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	87	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	HB 1.5	class mm	IEC 60695-11-10 -
ASTM Data			
DTUL @ 66 psi	158	°C	ASTM D 648
DTUL @ 264 psi	110	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1400	kg/m ³	ISO 1183
Water Absorption, 24hr	0.33	%	ASTM D 570
Density	1400	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	200 - 215	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	175 - 190	°C	-
Zone 2	195 - 205	°C	-
Zone 3	210 - 220	°C	-
Screw speed	30 - 60	rpm	-

Back pressure

0.2 - 0.3

MPa

-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific