

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	15	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Melt flow index, MFI	20	g/10min	ISO 1133

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	4800	MPa	ISO 527
^[C] Stress at break	61	MPa	ISO 527
^[C] Strain at break	5	%	ISO 527
Flexural modulus, 23°C	4800	MPa	ISO 178
^[C] Charpy notched impact strength, +23°C	3	kJ/m ²	ISO 179/1eA

ASTM Data

Tensile Strength	60	MPa	ASTM D 638
Elongation at Break	7	%	ASTM D 638
Flexural Modulus	5000	MPa	ASTM D 790
Flexural Strength	108	MPa	ASTM D 790
Rockwell Hardness	M 98	-	ASTM D 785
Izod Impact notched, 1/8 in	39	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	131	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	161	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	60	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

ASTM Data

UL 94 Flame rating	HB	-	UL 94
Coefficient of Thermal Expansion, MD	60	E-6/K	ASTM D 696
DTUL @ 66 psi	163	°C	ASTM D 648
DTUL @ 264 psi	150	°C	ASTM D 648

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1580	kg/m ³	ISO 1183
Water Absorption, 24hr	0.2	%	ASTM D 570
Density	1580	kg/m ³	ASTM D 792

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	180 - 210	°C	-
Mold temperature	60	°C	-

Characteristics

TENAC™-C MT754

POM-MF20

Asahi Kasei

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Features

Low Warpage, Copolymer

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa