

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>10</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
Molding shrinkage, parallel	<b>1.1</b>	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>6700</b>	MPa	ISO 527
Tensile Strength	<b>58</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>5500</b>	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>110</b>	°C	ISO 75-1/-2
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
<b>Electrical properties</b>			
<b>ISO Data</b>			
Surface resistivity	<b>1E14</b>	Ohm	IEC 62631-3-2
<b>Other properties</b>			
Density	<b>1660</b>	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	<b>75</b>	°C	-
Pre-drying - Time	<b>2 - 8</b>	h	-
Melt temperature	<b>200</b>	°C	-
Mold temperature	<b>80 - 120</b>	°C	-
Zone 1	<b>175 - 190</b>	°C	-
Zone 2	<b>185 - 205</b>	°C	-
Zone 3	<b>180 - 200</b>	°C	-
Nozzle temperature	<b>175 - 200</b>	°C	-

## Characteristics

### Processing

Injection Molding

### Features

Low Warpage, Tribologic Grade

### Delivery form

White

### Applications

Automotive, IT / Business Machine

### Additives

Lubricants

### Regional Availability

North America, Europe, Asia Pacific