

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	15	g/10min	ISO 1133
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	86	MPa	ISO 527
Strain at break	2.7	%	ISO 527
Flexural modulus, 23°C	4800	MPa	ISO 178
Charpy notched impact strength, +23°C	3.6	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	152	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	60	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Surface resistivity	>1E15	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Humidity absorption	0.23	%	Sim. to ISO 62
Density	1590	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	60 - 80	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.1	%	-
Mold temperature	60 - 80	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	170 - 180	°C	-
Zone 2	180 - 190	°C	-
Zone 3	190 - 200	°C	-
Nozzle temperature	180 - 210	°C	-
Back pressure	2	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific

**Features**

Low Warpage