

PULSE™ GX90

(PC+ABS)

Trinseo

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	17	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2200	MPa	ISO 527
Yield stress	50	MPa	ISO 527
Strain at break	>50	%	ISO 527
Charpy notched impact strength, +23°C	55	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	55	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	106	°C	ISO 75-1/-2
Vicat softening temperature, B	123	°C	ISO 306
Coeff. of linear therm. expansion, normal	75	E-6/K	ISO 11359-1/-2

Other properties	Value	Unit	Test Standard
Density	1120	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	255 - 275	°C	-
Mold temperature	70 - 80	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Features

Blending Resin, Low Odor

Applications

Automotive

Regional Availability

Europe, Near East/Africa