

## Petrothene XL07425

PO

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break	17.2	MPa	ASTM D 412
Elongation at Break	240	%	ASTM D 412

  

Other properties	Value	Unit	Test Standard
Density	1400	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Wire/Cable Extrusion

#### Special Characteristics

Flame retardant, Halogen-free

#### Features

Crosslinkable

#### Applications

Automotive, Electrical and Electronical

#### Regional Availability

North America, Europe, Asia Pacific, Near East/Africa