

Stat-Tech™ ATC-000/000 AS BLACK

POM

Avient Corporation

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2500	MPa	ISO 527
Stress at break	55	MPa	ISO 527
Strain at break	18	%	ISO 527
Charpy impact strength, +23°C	85	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA

Electrical properties	Value	Unit	Test Standard
ISO Data			
Surface resistivity	1E11	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1390	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Black

Special Characteristics

Anti-static

Features

Copolymer

Regional Availability

Europe