

**Product Texts**

Polypropylene, 20% glass beads and 20% mineral filled, laser printable, low emission

Flammability @3.2mm nom. thickn. HB -  
 Flammability @1.6mm nom. thickn. HB -

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
[C] Tensile Modulus	3400	MPa	ISO 527
[C] Charpy impact strength, +23°C	16	kJ/m <sup>2</sup>	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	2.1	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
[C] Temp. of deflection under load, 1.80 MPa	72	°C	ISO 75-1/-2
[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Density	1230	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Europe, Asia Pacific, Near East/Africa

**Features**

Laser Markable, Low Emission