

Product Texts

Polypropylene, copolymer, hollow glass bubbles reinforced, low density.

Flammability @3.2mm nom. HB
thickn. -

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2200	MPa	ISO 527
^[C] Charpy impact strength, +23°C	18	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	68	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	63	°C	ISO 306

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	800	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Copolymer

Delivery form

Black