

**SABIC® PPcompound G3010A**

PP-GF10

Saudi Basic Industries Corporation (SABIC)

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>0.2</b>	g/10min	ISO 1133
Molding shrinkage, parallel	<b>1.1</b>	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>2400</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>2200</b>	MPa	ISO 178

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>90</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>140</b>	°C	ISO 75-1/-2

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>960</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Features**

Chemically Coupled Reinforcement, Creep Resistance, Copolymer, Random Copolymer