

**Product Texts**

Polypropylene, copolymer, 15% glass fiber reinforced, chemically coupled, heat stabilised, UL listed V0

Flammability @3.2mm nom. thickn. V-0 -  
 Flammability at thickness h (1.5 mm) V-0 UL recognition (h)

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Charpy impact strength, +23°C	<b>45</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>11</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Burning Behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-
Yellow Card available	<b>yes</b>	-	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	<b>1360</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Features**

Chemically Coupled Reinforcement, Copolymer

**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

**Regional Availability**

Europe, Asia Pacific, Near East/Africa