POLIFOR® L30 GF/20 H

PP-GF20 Celanese

Product Texts

Polypropylene, homopolymer, 20% glass fiber reinforced, chemically coupled, heat stabilised

Flammability @3.2mm nom. thickn.	HB	-
Flammability @1.6mm nom. thickn.	HB	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	**4500**	MPa	ISO 527
[C] Stress at break	**70**	MPa	ISO 527
[C] Strain at break	**3.5**	%	ISO 527
[C] Charpy notched impact strength, +23°C	**7.5**	kJ/m²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
[C] Temp. of deflection under load, 1.80 MPa	**138**	°C	ISO 75-1/-2
[C] Burning Behav. at 1.5 mm nom. thickn.	**HB**	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Density	**1040**	kg/m³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Features

Chemically Coupled Reinforcement, Homopolymer

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe, Asia Pacific, Near East/Africa

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.