

Product Texts

Elastomer modified polypropylene copolymer, 20% glass fiber reinforced, chemically coupled, high UV resistance

Flammability @3.2mm nom. thickn. HB -
 Flammability @1.6mm nom. thickn. HB -

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3300	MPa	ISO 527
^[C] Yield stress	45	MPa	ISO 527
^[C] Yield strain	5.5	%	ISO 527
^[C] Charpy impact strength, +23°C	68	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	26	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	100	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1040	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Features

Chemically Coupled Reinforcement, Copolymer

Regional Availability

Europe, Asia Pacific, Near East/Africa