

Polimaxx 2511HX GA5

PP-GF25

IRPC

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.1	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	63.3	MPa	ASTM D 638
Elongation at Break	7	%	ASTM D 638
Flexural Modulus	4807	MPa	ASTM D 790
Rockwell Hardness	R 96	-	ASTM D 785
Izod Impact notched, 1/8 in	201	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	159	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1070	kg/m ³	ASTM D 792

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 85	°C	-
Pre-drying - Time	2 - 3	h	-
Melt temperature	190 - 240	°C	-

Characteristics**Processing**

Other Extrusion

Special Characteristics

Heat stabilized or stable to heat

Features

Copolymer

Applications

Automotive, Electrical and Electronical

Regional Availability

Europe, Asia Pacific