

Product Texts

Laser Direct Structuring (LDS) *, Improved Impact

ISO 1043 (PC+ABS)

[XANTAR Polycarbonate & Blends, your global partner for innovative added value](#)

**The compound is intended specifically for the use in the process of manufacturing conducting path designs according to the German application of the patent 101 32 092 of LPKF Laser & Electronics AG (Osteriede 7 30827 Garbsen Germany). Please address straight to LPKF Laser & Electronics AG (www.LPKF.de).*

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2250	MPa	ISO 527
^[C] Yield stress	49	MPa	ISO 527
^[C] Yield strain	4	%	ISO 527
^[C] Nominal strain at break	>50	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
^[C] Puncture energy, +23°C	35	J	ISO 6603-2

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	100	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	122	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	70	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	70	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1230	kg/m ³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	270	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 120	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.03	%	-

XANTAR™ LDS 3724

(PC+ABS)

Mitsubishi Engineering-Plastics Corporation

Melt temperature	270 - 300	°C	-
Mold temperature	80 - 120	°C	-
Zone 1	260 - 280	°C	-
Zone 2	270 - 290	°C	-
Zone 3	270 - 300	°C	-
Nozzle temperature	270 - 290	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Platable

Delivery form

Pellets

Regional Availability

Europe, Asia Pacific

Additives

Release agent

Other text information**Injection molding**[Injection Molding Recommendations](#)