OMNIPRO® HPP GRC30

PP-GF30 Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	**7200**	MPa	ISO 527
[C] Stress at break	**75**	MPa	ISO 527
[C] Strain at break	**3**	%	ISO 527
[C] Charpy notched impact strength, +23°C	**11**	kJ/m²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Density	**1130**	kg/m³	ISO 1183

[C]: CAMPUS

Characteristics

Regional Availability

North America, South and Central America

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.