

Product Texts

Polypropylene, homopolymer, 30% glass fiber reinforced, chemically coupled, high flow, UV stabilised.

Flammability @3.2mm nom. thickn.	HB	-
Flammability @1.6mm nom. thickn.	HB	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	6800	MPa	ISO 527
^[C] Stress at break	90	MPa	ISO 527
^[C] Strain at break	2.8	%	ISO 527

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	148	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	136	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1120	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Chemically Coupled Reinforcement, Homopolymer

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

Europe, Asia Pacific, Near East/Africa