

PPC G30-300

PP-GF30

Polymer Technologies Services Inc

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength	55.2	MPa	ASTM D 638
Flexural Modulus	4137	MPa	ASTM D 790
Izod Impact notched, 1/8 in	80.1	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	157	°C	ASTM D 648
DTUL @ 264 psi	141	°C	ASTM D 648
Other properties			
Density	1130	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America

Delivery form

Pellets, Black