

RESLEN PPC8 GF30 UVHI NT 1B0000

PP-GF30

Polimarky Spółka Jawna

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	6000	MPa	ISO 527
Strain at break	2	%	ISO 527
Charpy impact strength, +23°C	40	kJ/m ²	ISO 179/1eU
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	140	°C	ISO 75-1/-2
Vicat softening temperature, A	155	°C	ISO 306
Other properties			
Density	1150	kg/m ³	ISO 1183

Characteristics**Delivery form**

Natural Color

Features

Copolymer

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

Europe