

Product Texts

Polypropylene copolymer, 30% glass fiber reinforced, chemically coupled, high flow.

Flammability @3.2mm nom. thickn. HB -

Flammability @1.6mm nom. thickn. HB -

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	6300	MPa	ISO 527
^[C] Stress at break	75	MPa	ISO 527
^[C] Strain at break	3.5	%	ISO 527
^[C] Charpy notched impact strength, +23°C	13.5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	146	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1120	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific, Near East/Africa

Features

Chemically Coupled Reinforcement, Copolymer