

Product Texts

High crystallinity polypropylene homopolymer reinforced with 35% chemically coupled glass fiber, high heat stabilization.

Flammability @3.2mm nom. thickn.	HB	-
Flammability @1.6mm nom. thickn.	HB	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	8400	MPa	ISO 527
^[C] Stress at break	100	MPa	ISO 527
^[C] Strain at break	3	%	ISO 527
^[C] Charpy notched impact strength, +23°C	12	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	152	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1180	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Features

Chemically Coupled Reinforcement, Homopolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa