

**Product Texts**

Base Polymer	Polypropylene Block Copolymer
Filler	40% glass fiber
Colour	black
Special Features	processing stabilized
Market Segment	Automotive, Various

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	12	cm <sup>3</sup> /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	7000	MPa	ISO 527
Tensile Strength	70	MPa	ISO 527
Strain at break	3	%	ISO 527
Charpy impact strength, +23°C	40	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	10	kJ/m <sup>2</sup>	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	1260	kg/m <sup>3</sup>	ISO 1183
Global warming potential	1.11	kg CO <sub>2</sub> eq./kg	ISO 14040, 14044

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Melt temperature	200 - 270	°C	-
Mold temperature	20 - 60	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Black

**Features**

Copolymer

**Certifications**

Recycled Resin Content

**Applications**

Automotive

**Regional Availability**

Europe