

OMNIPRO® HPP GRC40 LG

PP-GF40

Celanese

| Mechanical properties | Value | Unit | Test Standard |
|----------------------------------------------|--------------|-------------------|----------------------|
| ISO Data | | | |
| ^[C] Stress at break | 100 | MPa | ISO 527 |
| ^[C] Strain at break | 3 | % | ISO 527 |
| ^[C] Charpy impact strength, +23°C | 15 | kJ/m ² | ISO 179/1eU |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| ^[C] Density | 1240 | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics**Regional Availability**

North America, South and Central America