

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>4</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>113</b>	MPa	ASTM D 638
Flexural Modulus	<b>10900</b>	MPa	ASTM D 790
Flexural Strength	<b>168</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>151</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
Melting Temperature	<b>165</b>	°C	ASTM D 3418
<b>Other properties</b>			
<b>ASTM Data</b>			
Density	<b>1310</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
<b>ASTM Data</b>			
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>2</b>	h	-
Melt temperature	<b>190 - 230</b>	°C	-
Mold temperature	<b>60 - 80</b>	°C	-

**Characteristics**

**Processing**

Injection Molding

**Features**

Chemically Coupled Reinforcement, Homopolymer

**Delivery form**

Natural Color

**Regional Availability**

North America, Europe, South and Central America