

CELSTRAN® +PP-GF20-05CN05 Black

PP-GLF20

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	4300	MPa	ISO 527
^[C] Stress at break	76	MPa	ISO 527
^[C] Strain at break	2.5	%	ISO 527
^[C] Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1020	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Black

Special Characteristics

Heat stabilized or stable to heat

Features

Long fiber reinforced

Regional Availability

North America, Europe, Asia Pacific