

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>4400</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>85</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>2.4</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>45</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	<b>24</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>12</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>15</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>166</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>159</b>	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	<b>1030</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

Heat stabilized or stable to heat

**Features**

Long fiber reinforced

**Regional Availability**

North America, Europe, Asia Pacific