

CELSTRAN® PP-GF20-0553 AD9600R BLACK

PP-GLF20

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	4820	MPa	ISO 527
^[C] Charpy notched impact strength, +23°C	21	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1030	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Delivery form**

Black

Features

Long fiber reinforced